

### Description:

PAVIAIS A.C. consists of a two component (base and reactor) product based on polyurethane and acrylic resins. It hardens concrete pavements superficially and acts as anti-dust treatment. Used in interiors exclusively.

### Uses:

Applied on absorbent pavements like:

- Industrial warehouses
- Sports courts
- Laboratories
- Hospital rooms
- Computer rooms
- Exhibition halls
- Warehouses, Food Industry, etc.

### Features & benefits:

EXCELLENT MECHANICAL AND CHEMICAL RESISTANCE. EXCELLENT DURABILITY. EASY APPLICATION.

### Surface preparation:

The background of application must ensure proper setting, being dry, uniform, smooth, clean and free of grease, dust or loose particles.

### Application:

- Priming is done with IMPRIMAIS or IMPRIDUR in a single coating when the support is absorbent.
- Mix the two components in the following proportions at the moment to be used:  
Component "A" 1 part in weight  
Componente "B" 2 parts in weight
- Once priming is dry and the components are thoroughly mixed, the open time of the mix is 30 minutes.
- The first coating can be diluted to 50% and thus replace the primer.

### Technical Features:

- Density: component "B": 0.998 Kg/L  $\pm$  0.01
- : Great penetration into concrete by capillary movement.
  - : It confers great molecular cohesion to superficial particles.
  - : It prevents erosion and dust formation (anti-dust).
  - : It is resistant to grease, oils, acids, alkalis, solvents, aggressive water and oil.
- Solid content in volume: 38  $\pm$  1%
- : Resistant to the mechanical property of the support.
- Dry upon touching: 30 minutes at 20°C/65% R.H.
- Aspect: Smooth and textured depending on the type of sand.
- Colour/s: Rojo, verde, gris, negro and translucent.

### Coverage:

3 m<sup>2</sup> per kg.

The information provided on this technical data sheet and particularly the recommendations for the application and use of the product is based on our current knowledge and are provided in good faith, considering that the products are used, handled and stored under normal conditions and within the limits of its useful life. The possible differences between the materials, supports, and real conditions in the application site can be so important that it is no possible to establish a warranty with this document or any other information provided. The user must verify with a suitability test that the product conforms to the required use. Users should refer to the information included in the last technical data sheet edition.



#### PROFESSIONAL CONSTRUCTIVE SOLUTIONS

©TEAIS S.A. - All rights reserved - Avda. da Enerxía, nº 153, Pol. Ind. de Sabón - 15143 Arteixo, A Coruña  
Telf.: 981 600 966 - Fax: 981 601 508 - Email: info@teais.es



DIRECTION GÉNÉRALE  
Jonquet Face MTN Internet  
Tél.: (+229) 21 33 33 48  
95 96 00 08

04 B P : 0526 Cotonou  
contact@hbphenin.com  
www.hbphenin.com

DIRECTION COMMERCIALE  
HBP New City  
Moro Millaire à côté de l'axe Lobo  
Tél.: (+229) 21 32 43 48  
95 02 72 72 - 94 00 61 61

### Clean up:

Clean using our solvent DISOLVENTE DISOLUAIS.

### Packaging:

Available in packs of:

**Rojo:** 6 Kg  
30 Kg

**Negro:** 6 Kg  
30 Kg

**Others:** 6 Kg  
30 Kg

### Storage:

It is recommended to store this product for 1 year in tightly closed original packages kept away from fire and protected against bleakness.

### Health and safety advice :



The information provided on this technical data sheet and particularly the recommendations for the application and use of the product is based on our current knowledge and are provided in good faith, considering that the products are used, handled and stored under normal conditions and within the limits of it's useful life. The possible differences between the materials, supports, and real conditions in the application site can be so important that it is no possible to establish a warranty with this document or any other information provided. The user must verify with a suitability test that the product conforms to the required use. Users should refer to the information included in the last technical data sheet edition.