

Description:

MORIM consists of a pre-dosed mortar used for masonry jobs. It contains special additives that confer excellent mechanical resistance, waterproofing properties and workability.

Uses:

It is used in traditional renders, for setting up brick walls, concrete block walls, in basements, etc.

Features & benefits:

EXCELLENT WORKABILITY.PRE-DOSED.WATERPROOFING PROPERTIES.

Surface preparation:

The background of application must be clean, free of dust, loose particles, grease and oil. It is recommended to previously dampen the support in summer under high temperatures.

Application:

- Mix MORIM with water(approximately 200 cc for every kg of MORIM).
- Mix manually or by using a low speed mixer(300 to 400 r.p.m.).
- Before the application, leave to stand for 2 to 5 minutes.
- Apply using a small trowel in a conventional manner.
- Mix MORIM with water either manually or mechanically.
- Leave to stand for 2 to 5 minutes. The mix is then ready for application.
- Apply in the same manner as a traditional mortar, making it compact and finishing with a trowel.

TechnicalFeatures:

Water absorption: $18 \pm 2\%$
Adherence: $> 10 \text{ kg/cm}^2$
Colour/s: Blanco and gris
Compressive resistance: Approx. 150 kg/cm^2
Flexural strength resistance: $> 35 \text{ kg/cm}^2$
Powder density: $1.40 \pm 0.05 \text{ g/ml}$
Mass of density: $2,05 \pm 0.05 \text{ g/ml}$
Curing density: $1,80 \pm 0.05 \text{ g/ml}$

Coverage:

2 kg/m² for every mm of thick layer.

Clean up:

Clean using large amounts of water.

Storage:

It is recommended to store this product for 2 years in its tightly closed original packages protected against bleakness.

The information provided on this technical data sheet and particularly the recommendations for the application and use of the product is based on our current knowledge and are provided in good faith, considering that the products are used, handled and stored under normal conditions and within the limits of its useful life. The possible differences between the materials, supports, and real conditions in the application site can be so important that it is no possible to establish a warranty with this document or any other information provided. The user must verify with a suitability test that the product conforms to the required use. Users should refer to the information included in the last technical data sheet edition.



PROFESSIONAL CONSTRUCTIVE SOLUTIONS

©TEAIS S.A. - All rights reserved - Avda. da Enerxía, nº 153, Pol. Ind. de Sabón - 15143 Arteixo, A Coruña
Telf.: 981 600 966 - Fax: 981 601 508 - Email: info@teais.es



DIRECTION GÉNÉRALE
Jonquet Face MTN Internet
Tél.: (+229) 21 33 33 48
35 96 00 08

04 B P : 0526 Cotonou
contact@hbphenin.com
www.hbphenin.com

DIRECTION COMMERCIALE
HBP New City
Moro Millaire & cste de Toullou
Tél.: (+229) 21 32 48 48
95 02 72 72 - 94 00 61 61

Packaging:

Available in packs of:

Blanco: 25 Kg

Gris: 25 Kg

Health and safety advice :



The information provided on this technical data sheet and particularly the recommendations for the application and use of the product is based on our current knowledge and are provided in good faith, considering that the products are used, handled and stored under normal conditions and within the limits of its useful life. The possible differences between the materials, supports, and real conditions in the application site can be so important that it is no possible to establish a warranty with this document or any other information provided. The user must verify with a suitability test that the product conforms to the required use. Users should refer to the information included in the last technical data sheet edition.



PROFESSIONAL CONSTRUCTIVE SOLUTIONS

©TEAIS S.A. - All rights reserved - Avda. da Enerxía, nº 153, Pol. Ind. de Sabón - 15143 Arteixo, A Coruña
Telf.: 981 600 966 - Fax: 981 601 508 - Email: info@teais.es



DIRECTION GÉNÉRALE
Jonquet Face MTN Internet
Tél.: (+229) 21 33 33 48
95 96 00 08

04 B.P. - 0526 Cotonou
contact@hbpbenin.com
www.hbpbenin.com

DIRECTION COMMERCIALE
HBP New City
Maison Militaire à côté de l'École
Tél.: (+229) 21 32 48 48
95 02 72 72 - 94 00 61 61