

1. DESCRIPTION Product Type

Xylazel Galvanised Metal Primer is a water based primer that promotes adhesion for metal finish paints on galvanised surfaces.

This primer produces a chemical reaction on galvanised surfaces turning them into a rough and black surface, ready to paint.

For interior and exterior use.

Advantages

- After applying Galvanised Metal Primer, surfaces stay perfectly protected.

- Water based formulation. No solvent required.

- Quick drying in just 1 hour.

- This product is ideal for any interior and exterior galvanised metal surfaces.

- It can be overcoated with any paint.

- Easy to apply: brush or spraying.

Colour

Transparent blue liquid.

Packaging 250 ml, 750 ml and 2 litres.

2. TECHNICAL DATA Coverage: 16-20 m²/litre.

Touch Dry: 1 hour.

Cleaning Equipment: water.

pH: 1-2

3. USAGE GUIDE Preparation

Surface must be suitably prepared, clean and dry, with dust, dirt, wax and grease removed. Remove all loose rust or dirt with a wire brush or sand paper. Test a small area first for coating adhesion and/or compatibility.

Application

Apply the product, covering all faces, sides and joints.

Allow the product to act for one hour.

After one hour surface must be rough and black.

Remove all loose dirt with water. Rinse thoroughly with clean water and allow time to dry.

Topcoat can be applied when Galvanised Metal Primer is dry.

4. OTHER INFORMATION

Do not store if the room temperature is below 5° C or over 30° C.

Do not empty into drains or water courses. Some local authorities have special facilities for disposing of waste coatings.

5. INFORMATION AND SERVICE

Whilst these specifications are based on expert technical knowledge and practical experience, we cannot assure responsibility for any work as the ultimate result depends on factors beyond our direct control.

Our Technical Services Department will be pleased to offer specific guidance or provide any further information you may require.



APARTADO 91 - GANDARAS DE PRADO, S/N 36400 PORRIÑO (PONTEVEDRA) TEL: + 34 986 34 34 24 FAX: + 34 986 34 64 17